

Application Serial No. 10/508,885
Reply to Office Action of July 24, 2008

PATENT
Docket: CU-3914

Amendments to the Claims

The listing of claims presented below replaces all prior versions, and listings, of claims in the application.

**RECEIVED
CENTRAL FAX CENTER**

OCT 23 2008

Listing of claims:

1. (withdrawn) A plaster board comprising:
 - a plaster core having a front surface, a back surface, two opposite side surfaces and two opposite end surfaces thereof, and
 - a covering base paper that covers the front surface, the back surface, and the two opposite side surfaces of the plaster core,
 - the plaster core comprising
 - a high-density hard edge part comprising the side surface covered with the covering base paper,
 - at least one high-density part comprising one of the front surface and the back surface covered with the covering base paper and having a density substantially equal to a density of the high-density hard edge part, and
 - a central low-density part having a density less than the densities of the high-density hard edge part and the high-density part and being inscribed in the high-density hard edge part and the high-density part,
 - wherein the high-density hard edge part is formed so as to be prevented from including a predetermined position at which a nail for fixing the plaster board is driven along the side surface.
2. (withdrawn) The plaster board as claimed in claim 1, wherein the high-density part has a thickness of 0.1 mm through 1.2 mm along a direction perpendicular to one of the front surface and the back surface.
3. (withdrawn) The plaster board as claimed in claim 2, wherein the high-density hard edge part has a thickness of at least 0.1 mm along a direction perpendicular to the side surface comprised in the high-density hard edge part.
4. (withdrawn) The plaster board as claimed in claim 2, wherein the high-density hard edge part has a thickness of 0.1 mm through 15.0 mm along a direction

Application Serial No. 10/508,885
Reply to Office Action of July 24, 2008

PATENT
Docket: CU-3914

perpendicular to the side surface comprised in the high-density hard edge part.

5. (currently amended) A method of fabricating a plaster board comprising:
- a plaster core having a front surface, a back surface, two opposite side surfaces and two opposite end surfaces thereof,
 - a front surface covering base paper that covers at least the front surface and the two opposite side surfaces of the plaster core, and
 - a back surface covering base paper that adheres to the front surface covering base paper and covers the back surface of the plaster core,
- in which the plaster core has a high-density hard edge part comprising the side surface,
- the method comprising the steps of:
- (a) pouring calcined plaster, water, at least one kind of additives and/or admixtures into a disk-type rotary mixer and stirring to prepare a calcined plaster slurry,
 - (b) extracting one portion of a slurry of the calcined plaster from at least one fractionation port provided on a peripheral area of the disk-type rotary mixer and providing the one portion of the slurry as a slurry for application onto the front surface covering base paper,
 - (c) spreading one portion of the slurry for application provided on the front surface covering base paper by a spreader roll to form a spread portion of the slurry for application while providing non-spread portions of the slurry for application at both sides of the spread portion,
 - (d) delivering the slurry of the calcined plaster remaining in the disk-type rotary mixer through a delivery pipe provided on the peripheral area of the disk-type rotary mixer to a delivering port of the delivery pipe,
 - (e) pouring a foam into the remaining slurry of calcined plaster through one of the delivery pipe and a foam providing port set on the delivery pipe and uniformly dispersing the foam to prepare a slurry for core,
 - (f) depositing the slurry for core delivered from the delivering port onto the slurry for application applied on the front surface covering base paper, and
 - (g) folding the front surface covering base paper and adhering the back surface covering base paper to a margin of the front surface covering base paper to

Application Serial No. 10/508,885
Reply to Office Action of July 24, 2008

PATENT
Docket: CU-3914

form a stack and subsequently to dry the stack,

wherein a length of the spreader roll in axial directions is 98% through 108% of a distance between boundary lines of the front surface and the side surface and

a width of the non-spread portion is less than 10 mm, and

wherein the slurry for application for the non-spread portions in step (c) conducted prior to step (g) is applied to outsides of scoring lines of the front surface covering base paper which define a width of the plaster board.

6. (original) The method of fabricating a plaster board as claimed in claim 5, further comprising the step of providing the slurry for application onto the back surface covering base paper and spreading the slurry for application provided on the back surface covering base paper by a spreader roll.

7. (original) The method of fabricating a plaster board as claimed in claim 5, wherein a thickness of the spread portion is 0.2 mm through 1.5 mm.

8. (original) The method of fabricating a plaster board as claimed in claim 5, further comprising the step of adding water and a set retarder to the slurry for application.

9. (original) The method of fabricating a plaster board as claimed in claim 5, further comprising the step of adding a foam to the slurry for application.

10. (original) The method of fabricating a plaster board as claimed in claim 6, wherein a thickness of the slurry for application spread by the spreader roll, provided on the back surface covering base paper, is 0.2 mm through 1.5 mm.

11. (original) The method of fabricating a plaster board as claimed in claim 6, further comprising the step of adding water and a set retarder to the slurry for application to be provided onto the back surface covering base paper.

12. (original) The method of fabricating a plaster board as claimed in claim 6, further comprising the step of adding a foam to the slurry for application to be

Application Serial No. 10/508,885
Reply to Office Action of July 24, 2008

PATENT
Docket: CU-3914

provided onto the back surface covering base paper.

13. (previously presented) The method of fabricating a plaster board as claimed in claim 5, wherein the length of the spreader roll in axial directions is 99% through 108% of a distance between boundary lines of the front surface and the side surface.

14. (cancelled)

15. (new) The method of fabricating a plaster board as claimed in claim 5, wherein the length of the spreader roll in axial directions is 100% through 108% of a distance between boundary lines of the front surface and the side surface.

16. (new) The method of fabricating a plaster board as claimed in claim 5, wherein a length of the hard edge part in directions of a width thereof on a cross section thereof in directions of a width of a hardened plaster board after drying in step (g) is about 0.1 mm to about 15.0 mm and a shape thereof is selected from the group consisting of a triangular shape, a crescentic shape, an L-shape, and a J-shape.